

REMARKS

Upon entry of this Amendment, claims 1-22 will be pending, of which claims 1, 6 and 12 are independent. The claims have been amended to eliminate multiple dependencies and to employ a more conventional U.S. claim format. In addition, the specification has been amended to include a cross reference to the PCT parent application. It is respectfully submitted that no new matter has been introduced.

It is respectfully submitted that the Application is in condition for allowance and a Notice to that effect is courteously solicited. If any questions remain, however, the Examiner is encouraged to call undersigned to expedite the prosecution of this Application.

Respectfully submitted,

PILLSBURY WINTHROP LLP

By: Richard A. Steinberg

Richard A. Steinberg

Reg. No.: 26,588

Paul L. Sharer

Reg. No. 36,004

Tel. No.: (703) 905-2039

Fax No.: (703) 905-2500

PLS/RAS:cdw
1600 Tysons Boulevard
McLean, VA 22102
(703) 905-2000

10025684-122601

APPENDIX

I. VERSION WITH MARKINGS TO SHOW CHANGES MADE

IN THE SPECIFICATION:

A cross-reference to the PCT parent application has been added.

IN THE CLAIMS:

Claims 4, 5, 7-9, 11, 14-17 and 19-22 have been amended as follows:

4. (Amended) Polymer composition according to [any one of claims 1-3, characterised in that] claim 1, wherein the polymer composition is essentially [halogen free] halogen-free.
5. (Amended) Polymer composition according to [any one of claims 1-4] claim 1, comprising between 2 and 5 wt. % antimony trioxide with an average particle size of at least 1.5 [micrometer] micrometers.
7. (Amended) Polymer composition according to [any one of claims 1-6, characterised in that it contains] claim 1, containing between 0.5 and 3 wt. % antimony trioxide and between 0.1 and 3 wt. % nacreous pigment.
8. (Amended) Polymer composition according to [any one of claims 1-7, characterized in that] claim 1, wherein the weight ratio of the nacreous pigment and the antimony trioxide lies between 1:5.5 and 1:50.
9. (Amended) Polymer composition according to [any one of claims 1-8, characterized in that] claim 1, wherein the polymer composition is essentially [halogen free] halogen-free and contains a halogen-free flame retardant.

11. (Amended) Article, wholly or partly made of the polymer composition according to [any one of claims 1-10] claim 1.

14. (Amended) Process according to [any one of claims 12-13] claim 12, wherein the polymer composition contains between 0.5 and 5 wt. % of antimony trioxide.

15. (Amended) Process according to [any one of claims 12-14] claim 12, wherein the polymer composition is essentially [halogen free] halogen-free.

16. (Amended) Process according to [any one of claims 12-15] claim 12, wherein the polymer composition contains between 2 and 5 wt. % antimony trioxide with an average particle size of at least 1.5 micrometers [micrometer].

17. (Amended) Process according to [any one of claims 12-16] claim 12, wherein the polymer composition is essentially [halogen free] halogen-free and contains a halogen-free flame retardant.

19. (Amended) Process for applying a dark laser marking onto a light background, which comprises irradiating [in which] an article consisting, at least at the place where the marking is applied, of a polymer composition according to [any one of claims 1-10 is irradiated] claim 1 with a laser light in the pattern of the marking.

20. (Amended) Process according to [any one of claims 12-19, characterized in that] claim 12, wherein the article is irradiated with laser light with a wavelength of 1064 nm.

21. (Amended) Process according to [any one of claims 12-20, characterized in that] claim 12, wherein the article is irradiated with laser light from a diode-pumped laser.

22. (Amended) Process according to [any one of claims 12-21, characterized in that] claim 12, wherein the article is radiated with laser light from an Nd:YAG laser.

10025684-122601